



BUOYANCY[®]
IMPEX PVT. LTD.

- 📍 "C" Tower, 10th Floor, Hampton Park, Vesu, Surat 395007 Gujarat, India
- ☎ +91 99250 53193
+91 99250 53069
- ✉ info@buoyancyimpex.com
buoyancyinc@gmail.com

Base oil N-70 (Group II)

Group II are hydro-cracked base oils. They are produced by undergoing hydro-processing which increases the level of saturates and purges out impurities. They have fair to good performance in lubricating properties such as volatility, oxidative stability and flash/fire points. They have only fair performance in areas such as pour point, cold crank viscosity and extreme pressure wear. They are defined as having a viscosity index between 80 and 120 while having a level of sulphur lower than 0.03% and are less polar with values less than 10 pS/m very low conductivity

Applications

- 1) Transformer oil, ink oil
- 2) Marine oil
- 3) Industrial gear oil
- 4) Automatic transmission fluid
- 5) White oil, process oil
- 6) Gear oil, Axle oil

Parameter	Unit	Test Method	Value
Color	-	ASTM D 1500	0.5 Max
Density at 15°C	(g/ml)	ASTMD 1298	0.82-0.88
Kinematic Viscosity at 100°C	(cSt)	ASTMD 445	2.5-3.5
Kinematic Viscosity at 40°C	(cSt)	ASTMD 445	9-12
Viscosity Index	-	ASTM D2270	80 Min
Pour Point	(°C)	ASTM D 97	-25Min
Flash Point	(°C)	ASTM D 92	160 Min
Carbon Residue	Wt%	ASTM D 524	0.06 Max
Sulphur	Wt%	ASTMD 5453	0.001 Max
Saturates	Wt%	ASTM D 7419	99.9 Min
Aromatics	Wt%	ASTM D 7419	1 Max
Appearance	Visual	...	Clear and Bright

Advantages

- 1) Better oxidation control and Improved NOACK stability
- 2) Enhanced viscosity control and Better base number retention
- 3) Priced very close to Group I oils
- 4) Reduces wear on engine components
- 5) Results in an extended range before changing lubricants

Accredited: ISO9001:2015 | ISO 14001:2015 | ISO45001:2018