



 "C" Tower, 10th Floor, Hampton Park,
 Vesu, Surat 395007 Gujarat, India
 +91 99250 53193
 +91 99250 53069
 info@buoyancyimpex.com
 buoyancyinc@gmail.com

Viscosity Grade Bitumen VG-30

Viscosity grade bitumen has a thermoplastic property which causes the material to soften at high temperatures and to harden at lower temperatures. This unique temperature/ viscosity relationship is important when determining the performance parameters such as the adhesion, rheology, durability and application temperatures of bitumen. In the Viscosity Graded Bitumen specifications, further special emphasize is placed on the Bitumen ductility.

The viscosity grading system is more rational than the penetration grading system. Viscosity is defined as the inverse of fluidity. Viscosity thus defines the fluid property of the bituminous material. Viscosity is the general term for consistency and it is a measure of resistance to flow.

To compare the specification of each grading system, it is necessary to find the equivalent grade of another system. The following table shows the equivalent penetration grades of viscosity grades with their general application.

| Standard | Grades Minimum Of Absolute | Viscosity, Poises@60°C | Equivalent Penetration grade |
|------------|----------------------------|------------------------|------------------------------|
| IS73: 2013 | VG-10 | 800 | 85-100 |
| | VG-20 | 1600 | ... |
| | VG-30 | 2400 | 60-70 |
| | VG-40 | 3200 | 30-40 , 40-50 |

| Property | Units | Results | Test method |
|--|--------|-----------|------------------|
| Penetration at 25°C, 100g, 5sec, Min | 0.1 mm | 45 | IS 1203 |
| Absolute viscosity at 60°C | P | 2400-3600 | IS 1206 (Part 2) |
| Kinematic viscosity at 135°C, Min | cSt | 350 | IS 1206 (Part 3) |
| Flash point (Cleveland open cup), Min | °C | 220 | IS 1448 [p : 69] |
| Solubility in trichloroethylene, Min | %Wt. | 99 | IS 1216 |
| Softening point (R&B), Min | °C | 47 | IS 1205 |
| Tests on residue from thin-film oven test | | | |
| Viscosity ratio at 60°C, Max | P | 4 | IS 1206 (Part 2) |
| Ductility at 25°C, Min | CM | 40 | IS 1208 |

According to viscosity (degree of fluidity) grading system, higher the grade, stiffer the bitumen, VG-30 BITUMEN is widely used in spraying applications such as surface dressing and paving in very cold climate in lieu of old 80/100 Penetration grade. It is also used to manufacture Bitumen Emulsion and Modified Bitumen products. Viscosity grade bitumen such as VG-10, VG-20, VG-30, VG-40 are produced as per IS73: 2013 standards

Accredited: ISO9001:2015 | ISO 14001:2015 | ISO45001:2018

 www.buoyancyimpex.com
 www.buoyancy.trustpass.alibaba.com